

# Data Sheet - Liquim®

## Liquim® - Bronze \*

Specification	Standard		Value		Variation	Unit
Basis Weight	ISO 536	150	210	290	+/- 8%	g/m <sup>2</sup>
Breaking length MD	ISO 1924-2	8,5	10,8	11,5	-	kN/m
Strain MD	ISO 1924-2	1,8	2,2	0,9	-	%
Breaking length CD	ISO 1924-2	2,5	3,0	3,3	-	kN/m
Strain CD	ISO 1924-2	3,3	4,4	4,6	+/- 3%	%
Gripping Qualities	NFQ 03 - 083	≥50	≥50	45		°
Burst	ISO 2759	352	441	465		kPa
Static friction - after 0,3 minute		1,12	1,12	1,12		
Static friction - after 3 minutes		2,3	2,3	2,3		
Cobb60 - Liquim side	ISO 535	3	3	3	+/-10%	g/m <sup>2</sup>
Cobb60 - Test liner side	ISO 535	34	34	34	+/- 10%	g/m <sup>2</sup>

\*Recommended maximum storage: 12 months



Environmentally friendly - 100 % recycled  
As we use recycled paper/cardboard, there may be colour differences.  
Coating: Water-based emulsion.

# Data Sheet - Liquim<sup>®</sup>

## Liquim<sup>®</sup> - Silver\*

Specification	Standard		Value		Variation	Unit
Basis Weight	ISO 536	155	215	295	+/- 8%	g/m <sup>2</sup>
Breaking length MD	ISO 1924-2	8,5	10,8	11,5	-	kN/m
Strain MD	ISO 1924-2	1,8	2,2	0,9	-	%
Breaking length CD	ISO 1924-2	2,5	3,0	3,3	-	kN/m
Strain CD	ISO 1924-2	3,3	4,4	4,6	+/- 3%	%
Gripping Qualities	NFQ 03 - 083	≥50	≥50	45		°
Burst	ISO 2759	352	441	465		kPa
Static friction - after 0,3 minute		1,12	1,12	1,12		
Static friction - after 3 minutes		2,3	2,3	2,3		
Cobb60 - Liquim side	ISO 535	3	3	3	+/-10%	g/m <sup>2</sup>
Cobb60 - Antim side	ISO 535	15	15	15	+/- 10%	g/m <sup>2</sup>

\*Recommended maximum storage: 12 months



Environmentally friendly - 100 % recycled  
As we use recycled paper/cardboard, there may be colour differences.  
Coating: Water-based emulsion.

# Data Sheet - Liquim<sup>®</sup>

## Liquim<sup>®</sup> - Gold\*

Specification	Standard		Value		Variation	Unit
Basis Weight	ISO 536	165	230	310	+/- 8%	g/m <sup>2</sup>
Breaking length MD	ISO 1924-2	8,5	10,8	11,5	-	kN/m
Strain MD	ISO 1924-2	1,8	2,2	0,9	-	%
Breaking length CD	ISO 1924-2	2,5	3,0	3,3	-	kN/m
Strain CD	ISO 1924-2	3,3	4,4	4,6	+/- 3%	%
Gripping Qualities	NFQ 03 - 083	≥50	≥50	45		°
Burst	ISO 2759	352	441	465		kPa
Static friction - after 0,3 minute		1,12	1,12	1,12		
Static friction - after 3 minutes		2,3	2,3	2,3		
Cobb60 - Liquim side	ISO 535	3	3	3	+/-10%	g/m <sup>2</sup>
Cobb60 - Liquim side	ISO 535	3	3	3	+/- 10%	g/m <sup>2</sup>

\*Recommended maximum storage: 12 months



Environmentally friendly - 100 % recycled  
As we use recycled paper/cardboard, there may be colour differences.  
Coating: Water-based emulsion.